

## Ventiflex specifications 2020

	VENTIFLEX 6220FR	VENTIFLEX 6212FR	VENTIFLEX 6298FR	VENTIFLEX 6698FR	VENTIFLEX 7111FRAS	VENTIFLEX 7198FRAS	VENTIFLEX 7117FRAS
<b>1. Total weight</b>							
<b>g/m<sup>2</sup>:</b>	650	620	685	735	800	850	620
<b>2. Tensile strength</b>							
<b>acc. to EN 12311-2 N/5cm</b>							
<b>warp approx.:</b>	1745	1745	1830	1830	1800	1940	1745
<b>weft approx.:</b>	1850	1850	2100	2600	2000	2180	1850
<b>3. Tear strength trapezoid</b>							
<b>acc. to EN 12310-2 N</b>							
<b>warp:</b>	450	450	530	530	500	600	450
<b>weft:</b>	600	600	700	850	600	700	600
<b>4. Fire resistant</b>							
<b>Hor.:DIN 75200/ISO3795</b>	DIN 75200	DIN 75200	SS-EN13501	SS-EN13501	DIN 75200/ ISO3795	DIN 75200/ EN11925-2	DIN 75200/ ISO 3795 UNI9177
<b>Ver.:SS-EN13501-1 or EN-ISO11925</b>							
<b>5. Yarn</b>	PES	PES	PES	PES	PES	PES	PES
<b>Dtex</b>	1100/1670	1100/1670	1100/1670	1100/2200	1100/1670	1100/1670	1100/1670
<b>6. Surface resistivity</b>					$\leq 3 \cdot 10^8 \Omega$	$\leq 1 \cdot 10^8 \Omega$	$\leq 3 \cdot 10^8 \Omega$
<b>acc. to DIN 53482</b>							
<b>7. Temperature range storage</b>	-40 to +70C	-40 to +70C	-40 to +70C	-40 to +70C	-40 to +70C	-40 to +70C	-40 to +70C
<b>8. Certified</b>	ISO 9001 / ISO 14001	ISO 9001 / ISO 14001	ISO 9001 / ISO 14001	ISO 9001 / ISO 14001	ISO 9001 / ISO 14002	ISO 9001 / ISO 14003	ISO 9001 / ISO 14004